

REVISION OF SECTION 703
AGGREGATE FOR PLANT MIX PAVEMENTS

Section 703 of the Standard Specifications is hereby revised for this project as follows:

Subsection 703.04 shall include the following:

The aggregate for Hot Mix Asphalt (HMA) shall meet the requirements of Table 703-3A when tested in accordance with CP-L 4211 Resistance of Coarse Aggregate to Degradation by Abrasion in the Micro-Deval Apparatus. The Contractor shall be assessed a price reduction of \$1000 for each production sample of the combined aggregate with a value greater than 20 according to CP-L 4211. A minimum of 5 samples shall be run.

Table 703-3A
AGGREGATE DEGRADATION BY ABRASION
IN THE MICRO-DEVAL CP-L 4211

	Not to exceed
Combined Aggregate (Mix Design)	18
Combined Aggregate (1/10,000 tons, minimum of 5 per project during production)	20